

Magicol Violet RLR

Dioxazine

C.I. Pigment Violet 23
Colour Index No. 51319



Technical Application Data

	HDPE	PVC
Heat Stability(C°)	280	—
Light Fastness SD $\frac{1}{3}$ Full Shade	8	8
Light Fastness SD $\frac{1}{3}$ Reduction	8	8
Weather Fastness SD $\frac{1}{3}$ Full Shade	4-5	4-5
Weather Fastness SD $\frac{1}{3}$ Reduction	4	4-5
Fastness to bleed	—	4

Physical Characteristics

CAS No:	6358-30-1
Density(g/cm ³)	1.48
Alkali resistance	5
Acid resistance	5
Specific surface(m ² /g)	84

Range of Applications

						Spin Dyeing	
LDPE	●	PP	●	PC	—	PP	●
HDPE	●	Rubber	●	PBT	—	PET	—
PUR	●	PS/SAN	●	PA	●	PA	●
PVC	●	ABS	●	POM	—	PAN	●

Commentary

A brilliant violet pigment, slightly reddish. Very high color strength, fastness properties. Not recommended as tinting component, for a conceivable sharp depression of heat resistance and migration. In combination with phthalocyanine pigments it is possible to economically match navy shades.

Note : Data Presented above is based on our present knowledge and is with intentions of providing general guidelines for use of our products. These products are offered by TINTEC without any kind of guarantee. We recommend that customers should test the suitability of these products in their end application before use.